

KRYTEX MEGA 8

Composite protective coating for paint

Packaging: 50 ml

Enough for: ≈ 3 cars

A composite coating: darker, richer paint color, a "harder" top layer and a slick surface. Use on its own or as a top coat over KRYTEX 9H+.



KEY PROPERTIES

- Reduces dirt build-up and makes cleaning easier.
- Protects paint from fading and keeps its natural color.
- Increases the "hardness" of the paint's top layer.
- Lowers the risk of damage from harsh car-wash chemicals and unskilled staff.
- Deepens and enriches paint color.
- Makes the surface slick.
- Reduces the likelihood of chips.
- Lowers the risk of corrosion forming and spreading.

SPECIFICATIONS

Contact angle	118°	Acid/alkali resistance	pH 1–14
Service life	up to 12 months	Solvent resistance	Aliphatic and aromatic solvents
Layer thickness	60–80 nm	UV resistance	10–400 nm
Consumption	1–2 ml/m ²	Wash resistance	up to 65 washes / 25,000 km
Application	Body paint	Volume	50 ml
Cure before delivery	≥ 8 h	Enough for	≈ 3 cars
Hardness (Mohs / Shore)	3.5 / 92–93		

HOW TO APPLY

- 01** Two-phase wash; remove tar, oil stains and iron fallout, then clay the paint to lift remaining contamination.
- 02** Polish the paint.
- 03** Degrease thoroughly with KRYTEX DEGREASER.
- 04** Load the applicator with 10–15 drops; add 3–5 drops as you go.
- 05** Apply in small sections of 40×40–50×50 cm, cross-hatch.
- 06** 10–30 s after application, when the coating starts to bead, buff to a gloss with a clean dry microfiber using moderate pressure.
- 07** Overlap the next section and buff the overlap carefully.
- 08** Use on its own or as a top coat over KRYTEX 9H+.
- 09** Cure at least 8 h before delivery.
- 10** Work at 15–25 °C and humidity no higher than 60%, out of direct sunlight and away from water.

COMPOSITION & STORAGE

Composition	Alkane solvent, fluorinated hydrocarbons, trimethylated silica, aminosilicone, polyorganosiloxane, tetraethoxysilane.
Shelf life	60 months
Storage	Keep tightly closed in the original container in a dry place at 0...+25 °C, away from direct sunlight. Do not use after the expiry date.

Data are based on laboratory tests and practical experience and are given for reference. Actual results depend on surface condition, application conditions and maintenance. Test on an inconspicuous area before use.

KRYTEX · krytex.world
Manufacturer: Guangzhou Keruitai Daily Chemical Technology Co., Ltd.
Europe: AR PRO Partners OÜ, Tallinn, Estonia